



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C07C 409/00, C08F 4/34, 14/06	A1	(11) International Publication Number: WO 99/05101 (43) International Publication Date: 4 February 1999 (04.02.99)
(21) International Application Number: PCT/EP98/04015 (22) International Filing Date: 16 June 1998 (16.06.98) (30) Priority Data: 97202307.1 24 July 1997 (24.07.97) EP (34) Countries for which the regional or international application was filed: NL et al. (71) Applicant (for all designated States except US): AKZO NOBEL N.V. [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): O. Boen, Ho [NL/NL]; Koekoekstraat 14, NL-3514 CW Utrecht (NL). WESTMI-JZE, Hans [NL/NL]; Burgemeester Boreellaan 1, NL-7437 BB Bathmen (NL). (74) Agent: SCHALKWIJK, Pieter, Cornelis; Akzo Nobel N.V., Patent Dept. (Dept. APTA), P.O. Box 9300, NL-6800 SB Arnhem (NL).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: EMULSIONS OF PEROXYESTERS (57) Abstract The invention relates to aqueous emulsions of peroxyesters comprising an anti-freeze agent, a polyvinyl acetate with a degree of hydrolysis between 45 and 68 %, and a non-ionic surfactant with an HLB value greater than 16 selected from alkylene oxide block-copolymers, ethoxylated fatty alcohols, and ethoxylated fatty acids. The emulsions are safe, storage stable, and generally applicable.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

EMULSIONS OF PEROXYESTERS

The invention relates to an aqueous emulsion of a peroxyester that is liquid at -20°C, which comprises a protective colloid, a non-ionic surfactant, and an
5 anti-freeze agent.

Such peroxide emulsions are known from EP-B-0 032 757. According to this reference, a variety of peroxides, colloids, and surfactants can be used in emulsions that also comprise an anti-freeze agent. For the surfactants and
10 protective colloids of choice, reference is made to US patent 3,988,261, which lists many such compounds. In respect of one of the listed types of protective colloids, viz. polyvinyl acetate (PVA), it is stated that the degree of hydrolysis will influence the properties. It is suggested to use PVAs with a substantial degree of hydrolysis, e.g. 65% or more. In EP-B-0 032 757, however, only
15 one emulsion is presented which includes a peroxyester, viz. tert.-butyl peroxyneodecanoate. In this example, an ethoxylated nonylphenol is used as the surfactant, while xanthan gum is used as the protective colloid.

The protective colloids and surfactants mentioned in US 3,988,261 generally
20 are not suitable for the production of concentrated, storage-stable, and safe peroxyester emulsions such as are widely accepted in polymerization processes. One type of surfactant, viz. the ethoxylated nonylphenols, is known to be detrimental to the electrical properties of polyvinyl chloride (PVC) when introduced into the polymerization process of vinyl chloride monomer
25 (VCM). Also, it is well-known that the ethoxylated nonylphenols have environmental drawbacks. In respect of the other surfactants that are listed, it is noted that they are generally unacceptable because they typically result in very viscous peroxyester emulsions and/or emulsions that are not safe, particularly when emulsions with a high concentration of perester are
30 produced. It was also found that most of the listed protective colloids, in combination with the suitable surfactants, are not acceptable in the

formulation of peroxyesters. The protective colloids mentioned will often result in unacceptable viscosity of the peroxyester emulsion.

Hence there is a need for concentrated peroxyester emulsions with a low viscosity that are storage-stable, safe, and generally applicable in polymerization processes, particularly those of VCM.

There are various other publications that relate to water-based peroxide dispersions. However, none of them disclose or suggest peroxyester emulsions that satisfy the above-mentioned criteria.

JP (61) 130315 (1986) suggests that peroxyester emulsions can be made using a protective colloid, a non-ionic surfactant, and an anti-freeze agent. It is taught that the non-ionic surfactant can be selected from a variety of materials, while the protective colloid must be a product with a high dissolution rate in water, such as modified celluloses and saponified polyvinyl acetates (PVAs). Preferred are PVAs with a degree of hydrolysis greater than 60 mole%. The only exemplified formulations are emulsions of peroxydicarbonates. Using these formulations for peroxyesters was found to result in emulsions that do not satisfy the requirements of safety, viscosity, and/or applicability.

GB 2 068 008 discloses aqueous peroxide dispersions wherein protective colloid such as celluloses or PVAs are used together with an emulsifier system with an HLB above 15. The emulsifier(s) is/are specified to be non-ionic, ethoxylated, free from cyclic internal ether bonds, and suitably selected from ethoxylated alkylphenols, ethoxylated fatty alcohols, ethoxylated fatty acids, ethoxylated glycol and glycerol fatty esters, and alkylene oxide block copolymers. Although this reference suggests using surfactants with a very high HLB value, it does not suggest to the skilled man that he should make a

specific combination of peroxyesters, anti-freeze, PVAs, and surfactants. More specifically, peroxyesters and/or anti-freeze agents are not mentioned at all.

- 5 We have now found that, surprisingly, improved aqueous peroxyester emulsions can be produced and applied by a proper combination of peroxyester, non-ionic surfactant, and protective colloid.

10 The invention is characterized in that the protective colloid is a polyvinyl acetate with a degree of hydrolysis between 45 and 68% and the non-ionic surfactant has an HLB value of 16 or higher and is selected from alkylene oxide block-copolymers, ethoxylated fatty alcohols, and ethoxylated fatty acids.

15 In this specification, the term "surfactant" refers to the surface-active chemical that is to be used in the peroxyester formulations according to the invention and that influences the interfacial surface tension between the water and the peroxyester phase. Such compounds are also known as "emulsifiers." Preferably, the aqueous peroxyester emulsion according to the invention
20 contains only one surfactant with an HLB value of 16 or higher. More preferred are surfactants with an HLB value of 17 or higher, since such surfactants tend to result in less viscous emulsions. If so desired, a mixture of surfactants can be used. In that case, the combined surfactants should have an HLB value of 16 or higher, while it is preferred that all surfactants used
25 have an HLB greater than 10, preferably greater than 12.5, and more preferably of 16 or higher, because surfactants with a lower HLB value can have an adverse effect on the viscosity of the final emulsion. HLB value stands for the hydrophilic-lipophilic balance as described in "The Atlas HLB-System, a time saving guide to emulsifier selection," published by Atlas
30 Chemical Industries Inc., 1963. For blends of surfactants the HLB value is

calculated from the weight ratio of the components, as is also mentioned in this publication.

The non-ionic surfactant or surfactants that can be used in the aqueous emulsions according to the invention are alkylene oxide block-copolymers, ethoxylated fatty alcohols, and ethoxylated fatty acids. The preferred surfactants are ethoxylated fatty alcohols and ethoxylated fatty acids with an HLB value greater than 16. Most preferred are such ethoxylated fatty alcohols. These products were found to be pre-eminently suited to make emulsions with good stability, safety, and viscosity properties at high peroxyester concentrations. The amount of the surfactant or the combination of surfactants in the final emulsion is from 0.05-5 percent by weight (%w/w). Preferably, from 0.1 to 2%w/w of surfactant is used, while an amount between 0.1 and 1%w/w is most preferred.

The protective colloid to be used in the aqueous emulsions according to the invention must be a PVA with a degree of hydrolysis between 45 and 68%. Preferably, the degree of hydrolysis is between 45 and 62.5%. Most preferred is a PVA with a degree of hydrolysis between 50 and 60%. A PVA with a degree of hydrolysis below 45% cannot be used because such a PVA is not soluble in the mixture of water and anti-freeze. A PVA with a degree of hydrolysis greater than 68% resulted in emulsions with a too high viscosity. Instead of using just one type of PVA, also a blend of two or more PVAs can be used. In that case the blend can be seen as just one PVA of which the degree of hydrolysis is the weight average degree of hydrolysis of the PVAs. Preferably, such a blend of PVAs does not comprise a PVA with a degree of hydrolysis below 45% or above 68%, for the above-mentioned reasons.

The amount of PVA used in the emulsions according to the invention will depend on the concentration and the types of peroxyester and surfactant

used and the desired viscosity of the final emulsion. Typically, the amount of PVA in the final emulsion will be between 0.5 and 10%w/w. The use of these protective colloids in combination with the above-mentioned surfactants allows the production of concentrated, storage-stable, and safe peroxyester emulsions.

The anti-freeze used in the emulsions according to the invention is to be used in an amount sufficient to keep the emulsion pourable and/or pumpable at a temperature of -20°C, while it is preferred that the emulsions are still fluid at temperatures of -25°C and lower. The amount of freezing point suppressant to be used will depend on the type of anti-freeze, or mixture of anti-freezes, that is used. Suitably, first a mixture of the anti-freeze and water is made which contains a sufficient amount of the anti-freeze to be pourable at the indicated temperatures. This mixture can then be used in the further process to make the emulsions. Although use can be made of most anti-freeze agents, such as salts and organic compounds, it is preferred to use organic compounds selected from methanol, ethanol, isopropanol, glycol, propanediol, and glycerol, since it is known that such compounds will have hardly any effect on polymerization processes in which peroxyester emulsions are used. Also combinations of two or more anti-freeze agents can be used in the emulsions according to the invention.

Peroxyester emulsions are considered to be concentrated when the amount of perester therein exceeds 30%w/w. Preferably, the concentration of peroxyester in the emulsions according to the invention is greater than 40%w/w. Even more preferred are emulsions containing 45-65%w/w of peroxyester. Most preferred are emulsions where the peroxyester concentration is 50 to 60%w/w, because such emulsions will allow substantially reduced freight and handling costs in comparison with emulsions containing 40%w/w or less of peroxyester. The safety aspects of the final

emulsion predominantly determine the high end of the peroxyester concentration range. More specifically, the water/anti-freeze content of the formulation should be sufficiently high to dissipate the heat of decomposition of the peroxyester.

5

The peroxyester emulsions according to the invention are suitable for most peroxyesters that are liquid at -20°C, but are particularly relevant for peroxyesters having a recommended storage temperature of 15°C or less. Typically, the recommended storage temperature is specified by the producer
10 of the peroxyesters, for instance, by Akzo Nobel Chemicals B.V. in the brochure "Initiators for high polymers" with code 10737. Peroxyesters preferably used in the aqueous emulsions according to the invention include:

- α -cumyl peroxyneodecanoate,
- 2,4,4-trimethylpentyl-2-peroxyneodecanoate
- 15 tert-amyl peroxyneodecanoate
- tert-butyl peroxyneodecanoate
- 2,4,4-trimethylpentyl-2-peroxypivalate
- tert-amyl peroxypivalate
- tert-butyl peroxypivalate
- 20 tert-butyl peroxyheptanoate
- 2,5-bis(2-ethylhexanoylperoxy)-2,5-dimethylhexane
- tert-amyl peroxy-2-ethylhexanoate, and
- tert-butyl peroxy-2-ethylhexanoate.

25 The emulsions according to the invention may, if so desired, comprise one or more thickeners in a concentration up to 2% by weight in order to control the viscosity of the composition. If used, the thickener preferably makes up less than 1% by weight of the emulsion. Non-limiting examples of thickeners useful in the formulation are xanthan gum, Arabic gum, and alginates.

30

Further to the above-mentioned compounds, the compositions according to the invention may also comprise other "standard" additives, including pH-adjusting agents such as calcium oxide or phosphate buffers, sequestering agents, and, if desired, biocides, e.g. fungicides. The concentration of these additives will depend on the desired effect and the other ingredients in the emulsion. Given the information presented here, the skilled man will have no problem selecting appropriate concentrations of the individual ingredients in the emulsions of choice.

What is meant by storage-stable emulsions is that the products do not freeze at storage temperatures of -20°C , preferably -25°C , and have an average peroxyester droplet size (d_{50}) and a 99 percentile of the droplet size distribution (d_{99}) which do not change by more than $20\text{ }\mu\text{m}$ during three months of storage. Preferably, the change in d_{50} is less than $10\text{ }\mu\text{m}$, more preferably less than $5\text{ }\mu\text{m}$, since changes in droplet size will influence the viscosity and further storage stability of the emulsion, while also the polymerization process can be adversely influenced when larger peroxyester droplets are introduced, e.g. by an increased number of fish-eyes. It is also for this reason that the d_{50} of the droplet size distribution should be below $20\text{ }\mu\text{m}$, while a d_{50} of less than $10\text{ }\mu\text{m}$, particularly below $5\text{ }\mu\text{m}$, is preferred. The particle size is determined by means of a light scattering technique, using a Malvern® Easy Sizer

As mentioned above, it is important that the concentrated peroxyester emulsions according to the invention have a viscosity that allows easy handling and use. In practice, this means that the product should have a viscosity of less than $500\text{ mPa}\cdot\text{s}$ when measured at 0°C using an Erichsen viscometer, model 332 ($0\text{--}500\text{ mPa}\cdot\text{s}$). Preferably, the Erichsen viscosity is less than $300\text{ mPa}\cdot\text{s}$, while less than $200\text{ mPa}\cdot\text{s}$ is most preferred. Alternatively, suitable emulsions were found to have a viscosity below 2000

mPa.s when measured at 0°C, using a Brookfield LVT with spindle sp3 at 12 rpm. Preferably, the emulsions will have a Brookfield viscosity of less than 1500 mPa.s.

- 5 As is well-known, peroxyesters are thermally labile organic compounds. Because the decomposition of peroxyesters is exothermic, it is hazardous when the heat of decomposition cannot be dissipated, e.g., by heat loss to the surrounding area. When heat build-up occurs, the decomposition reaction eventually becomes uncontrollable and potentially dangerous. To avoid such
- 10 undesired situations, the peroxide is typically formulated with one or more phlegmatizing agents, such as inert organic materials, including water. Aqueous peroxide emulsions are generally considered safe products because the peroxide is dispersed in the water phase, which is well-suited to the removal of the heat of decomposing peroxide molecules, e.g., by convection
- 15 and/or evaporation. However, it was observed that many peroxyester emulsions according to prior art formulations suffer from the draw-back that they show phase separation upon heating, particularly at temperatures where water evaporation becomes noticeable. If so, the peroxyester separates out and forms a highly concentrated peroxyester phase the heat of decomposition
- 20 of which is not dissipated. As a result, such aqueous peroxyester emulsions can be as hazardous as the neat peroxyester. One of the objects of the emulsions according to the invention therefore was to develop formulations that do not form a significant amount of a hazardous phase upon heating. More specifically, an emulsion is considered to be safe if less than 10% by
- 25 volume of one or more other phases is formed or, if more than 10% by volume of phase separation were to occur, none of the phases has a peroxyester content such that the active oxygen content is greater than 1%w/w. The emulsions as described herein were evaluated for safety by keeping them, for 8 hours, at a temperature which is 30°C above the well-
- 30 known self accelerating decomposition temperature (SADT) of the peroxide.

The emulsions of the invention can be produced in a conventional manner. Typically, the compounds of the emulsion are mixed and/or homogenized using well-known equipment, such as colloid mills, perl mills, pressure
5 homogenizers, fluidizers, ultrasonic homogenizers, etc. Because many of the peroxyesters are not stable at higher temperatures, the mixing and/or homogenizing should be done below a temperature of 15°C, preferably well below the SADT.

10 The emulsions of the invention are preferably used in suspension or emulsion polymerization processes. However, they can also be used in other processes, such as polymer modification processes, cross-linking reactions, mass polymerization processes, and curing processes of, for example, unsaturated polyester resins. In these processes a variety of monomers
15 and/or polymers can be reacted, including, for example, acrylates, vinyl esters, vinyl halides, vinyl ethers, vinyl aromatic compounds, such as styrene, lower alkenes, polybutadiene, methacrylate-butadiene-styrene copolymers and the like. The emulsions therefore can be used, for example, in the mass polymerization of vinyl chloride monomer (VCM). However, the emulsions are
20 more preferably used in suspension or emulsion polymerization processes wherein at least VCM, styrene or a (meth)acrylate is reacted. Most preferred is the use of the emulsions in the suspension polymerization process of predominantly VCM. The emulsions are only usable in these processes when they do not influence the properties of the resulting polymer, or do so only to
25 a very limited extent. In the preferred VCM polymerization process, this means that hardly any fouling is observed and the PVC particle size, porosity, fish-eye number, and electrical properties are hardly affected.

The peroxyester emulsions according to the invention and their uses are
30 further illustrated in the following examples.

Examples

In the examples, the following products and abbreviations were used:

5

LL02 = Gohsenol® LL02, a PVA ex Nippon Gohsei

55-2H = Alcotex® 55-2H, a PVA ex Revertex

UMR10M = Unitika® UMR10M, a PVA ex Unitika

552P = Alcotex 552P (as 100% active material) , a PVA ex Revertex

10

KP08 = Gohsenol KP08, a PVA ex Nippon Gohsei

KH17 = Gohsenol KH17, a PVA ex Nippon Gohsei

M05/190 = Polyviol® M05/190, a PVA ex Wacker

GH20 = Gohsenol GH20, a PVA ex Nippon Gohsei

Berol® 08 = ethoxylated stearyl alcohol ex Akzo Nobel (HLB=18.7)

15

Myrj® 53 = ethoxylated stearic acid ex ICI (HLB=17.9)

Softigen® 767 = ethoxylated capril/caprylic glyceride ex Hüls (HLB=18.0)

Tween® 20 = ethoxylated sorbitan monolaurate ex ICI (HLB=16.7)

Remcopal® 20 = ethoxylated lauryl alcohol ex Ceca (HLB=16.0)

Ethylan® R = ethoxylated cetyl/oleyl alcohol ex Akcros (HLB=15.4)

20

The peroxyesters as used in the examples were, typically, of industrial grade (crude reactor products). However, also purified peroxyesters can be used to make emulsions satisfying the criteria of the emulsions according to the invention.

25

Examples 1-4

An aqueous emulsion of 2,4,4-trimethylpentyl-2-peroxyneodecanoate was made by adding to a cooled vessel at -5°C:

- 50 percent by weight (%w/w) of 2,4,4-trimethylpentyl-2-peroxyneodecanoate (100% active material), supplied as industrial grade Trigonox® 151 with a purity greater than 85%,
 - 3.0%w/w of PVA (see table),
- 5 - 0.3%w/w of Berol 08 (an ethoxylated fatty alcohol, HLB=18.7),
- the remainder being a 76/24 mixture of water/methanol that did not freeze at -20°C. Next, the initiator was dispersed with an UltraTurrax® type S25N-25GM (4 minutes/kg of emulsion) at full power, during which the temperature of the solution/dispersion was kept 0-5 °C below the SADT of the initiator. In
- 10 Example 4, the amount of Berol 08 was reduced to 0.2%w/w.

Table 1

Example	1	2	3	4
PVA	LL02	55-2H	UMR10M	552P
hydrolysis (%)	45-51	54-57	62.6-67.5	54-57

After production

Erichsen (mPa.s)	385	345	borderline	250
Brookfield (mPa.s)	790	610	1600	360
d50/d99 (μm)	1.1/15.4	0.8/2.8	0.7/2.0	0.9/2.5

After 12 weeks storage

Erichsen (mPa.s)	315	265	420	no data
Brookfield (mPa.s)	1970	460	1080	no data
d50/d99 (μm)	5.2/36.3	2.9/4.3	2.5/3.4	no data

These emulsions are all acceptable. The emulsions according to Examples 2
5 and 4 are preferred.

Comparative Examples A-D

Example 1 was repeated using other types of PVA, with the following result:

10

Table 2

Comparative Example	A	B	C	D
PVA	KP08	KH17	M05/190	GH20
hydrolysis (%)	71-75	78-82	81-84	87-89

After production

Erichsen (mPa.s)	>500	>500	>500	>500
Brookfield (mPa.s)	5990	>10000	>10000	3030
d50/d99 (μm)	2.1/12.8	2.2/15.2	2.0/14.2	1.4/6.4

From these Examples 1-3 and Comparative Examples A-D it follows that only a PVA with a limited degree of hydrolysis can be used in the emulsions according to the invention.

5

Example 5 and Comparative Example E

In the emulsion of Example 1, the 2,4,4-trimethylpentyl-2-peroxyneodecanoate was replaced by α -cumyl peroxyneodecanoate, which was
 10 supplied as industrial grade Trigonox 99 of at least 80% purity.

Table 3

Example	5	E
PVA	552P	KP08
hydrolysis (%)	54-57	71-75

After production

Erichsen (mPa.s)	390	decomposed
Brookfield (mPa.s)	2000	during
d50/d99 (μm)	1.9/4.4	preparation

These examples confirm that stable and safe emulsions according to the
 15 invention can only be made using PVAs with a degree of hydrolysis in a specific range.

Examples 6-7

Example 5 was repeated, except that a 50:50 (by weight) mixture of Alcotex 552P (as 100% active material) and Unitika UMR10M was used as a protective colloid [Because the Alcotex contains 40% active material, 125 parts by weight of this PVA (as supplied) were combined with 50 parts by weight of the Unitika. It is noted that, for ease of reference, the amount that is used of the ingredients is presented as 100% pure materials throughout this specification]. In the following examples, the amount of PVA is, consequently, the total amount of 100% active material that is used. In Example 6 the amount of Berol 08 was reduced to 0.15%w/w.

Table 4

Example	6	7
amount of PVAs	1%w/w	1.5%w/w
average hydrolysis (%)	58.3-62.3	58.3-62.3

After production

Erichsen (mPa.s)	275	395
Brookfield (mPa.s)	950	borderline
d50/d99 (μ m)	1.2/4.0	2.7/4.0

After 12 weeks storage

Erichsen (mPa.s)	no data	140
Brookfield (mPa.s)	no data	750
d50/d99 (μ m)	no data	5.1/11.7

Both emulsions were safe. From these examples it follows that also combinations of PVA can be used as a protective colloid in the emulsions according to the invention.

5 Example 8 and Comparative Examples F and G

In the emulsion of Example 1, Alcotex 552P was used as the PVA, while the Berol 08 was replaced with the surfactants according to the table, with the following results.

10

Table 5

Example	8	F	G
Surfactant	Myrj 53	Softigen 767	Tween 20
HLB value	17.9	18.0	16.7

After production

Erichsen (mPa.s)	440	>500	495
Brookfield (mPa.s)	840	4260	3750
d50/d99 (µm)	7.1/28.2	25.7/92.3	24.4/98.9

The emulsion of Example 8 was safe. From these examples it follows that ethoxylated glyceryl esters of fatty acids (such as Softigen 767) and
 15 ethoxylated sorbitan esters (such as Tween 20), although they can have the desired HLB value, cannot be used in emulsions according to the invention.

Example 9 and Comparative Examples H and I

Example 1 was repeated, using the following recipe:

- 5 - 50%w/w tert-butyl peroxyneodecanoate (as 100%) supplied as industrial grade Trigonox 23,
 - 3.5%w/w of a 50:50 mixture of Alcotex 552P (as 100%) and Unitika UMR10M with an average degree of hydrolysis of 58.3-62.3%,
 - for Comparative Example H, 0.5%w/w of the non-ionic surfactant mentioned
 10 in the table, while in Comparative Example I, no surfactant was used, and
 - the remainder being a 74/26 mixture of water/methanol.

Table 6

Example	9	H	I
Surfactant	Remcopal 20	Ethylan R	None
HLB value	16.0	15.4	n.r.

After production

Erichsen (mPa.s)	480	>500	>500
Brookfield (mPa.s)	1440	>2000	1550
d50/d99 (μm)	1.2/6.0	0.7/5.0	0.7/5.9

- 15 The emulsion of Example 9 was safe, while the emulsion of Comparative Example I was unsafe. These examples show that surfactants of the proper type (an ethoxylated fat alcohol) cannot be used if the HLB value is below 16.0 and that the use of a surfactant is required.

Example 10 and Comparative Example J

An emulsion of 2,4,4-trimethylpentyl-2-peroxyneodecanoate was used in the polymerization of VCM in a 1liter stainless steel Büchi autoclave with 3-bladed stirrer, baffle, and temperature sensor. The polymerization recipe was as follows:

	VCM	260 g
	H ₂ O	520 g
10	KP-08	0.39 g
	Peroxyester emulsion	0.26 g (0.05%w/w of pure peroxide on VCM)
	Na ₂ HPO ₄	0.1 g
	NaH ₂ PO ₄	0.1 g

- 15 The PVA was dissolved in the water and the phosphate buffer was added. The reactor was evacuated and flushed with N₂ four times (at room temperature). While stirring at 735 rpm, VCM was added. Subsequently, the reactor was heated to 53.5 °C in 25 minutes. Then the initiator emulsion was added by injection through a septum. The polymerization was stopped after
- 20 480 minutes by venting off unreacted VCM and cooling. The PVC that was formed was filtered, washed with H₂) and dried overnight at 30°C in an air oven and analyzed. The conversion was determined gravimetrically, the mean particle size by means of a Coulter® Counter Multisizer, the bulk density with an Erichsen Din Cup 243/11.8, the dry flow with the same Din Cup, the
- 25 plasticizer absorption according to DIN 53417 and the fish-eye number as described by O. Leachs in Kunststoffe, Band 50(4), 1960, pp. 227-234.

- In Example 10 the emulsion of 2,4,4-trimethylpentyl-2-peroxyneodecanoate was the emulsion according to Example 4, while in Comparative Example J,
- 30 the emulsion was prepared by dispersing 50%w/w of peroxyester and 3%w/w of Unitika UMR10M in 47%w/w of 74/26 water/methanol. The viscosity of the

latter emulsion was not according to the invention. The result are presented below.

Table 7

Example	10	J
yield on VCM (%)	81.2	76.
fouling	none	some
PVC particles >800 μ m (g)	0.12	2.85
PVC bulk density (g/l)	374	404
PVC dry flow	3.02	3.36
PVC mean particle size (μ m)	126.7	139.0
fish-eye number (approx.)	50	100
DOP absorption (%)	29.5	26

5

These examples show that the emulsions according to the invention are very suitable for the production of PVC.

Claims

1. An aqueous emulsion of a peroxyester that is liquid at -20°C, comprising
5 a protective colloid, a non-ionic surfactant, and an anti-freeze agent, characterized in that the protective colloid is a polyvinyl acetate with a degree of hydrolysis between 45 and 68% and the non-ionic surfactant has an HLB value of 16 or higher and is selected from alkylene oxide block-copolymers, ethoxylated fatty alcohols and ethoxylated fatty acids.
- 10 2. An aqueous emulsion according to claim 1, characterized in that the peroxyester is present in an amount between 45 and 65% by weight.
- 15 3. An aqueous emulsion according to claim 1 or 2, characterized in that the polyvinyl acetate has a degree of hydrolysis between 45 and 62.5%, preferably between 50 and 60%.
- 20 4. An aqueous emulsion according to any one of the preceding claims, characterized in that the polyvinyl acetate is present in an amount between 0.5 and 10% by weight.
- 25 5. An aqueous emulsion according to any one of the preceding claims, characterized in that the surfactant is an ethoxylated fatty alcohol or an ethoxylated fatty acid.
6. An aqueous emulsion according to any one of the preceding claims, characterized in that the surfactant is present in an amount from 0.05 to 5% by weight, preferably 0.1-2% by weight.

7. An aqueous emulsion according to any one of the preceding claims, characterized in that the surfactant has an HLB value of 17 or higher.
- 5 8. An aqueous emulsion according to any one of the preceding claims, characterized in that the anti-freeze is a compound selected from the group consisting of methanol, ethanol, isopropanol, glycol, propanediol, glycerol, and combinations thereof, and is used in a quantity such that the emulsion does not freeze at a temperature of -20°C.
- 10 9. An aqueous emulsion according to any one of the preceding claims, characterized in that the average droplet size of the peroxyester in the emulsion is less than 20µm.
- 15 10. An aqueous emulsion according to any one of the preceding claims, characterized in that the viscosity of the emulsion is less than 500 mPa.s when analyzed with an Erichsen viscometer.
- 20 11. An aqueous emulsion according to any one of the preceding claims, characterized in that the viscosity of the emulsion is less than 2000 mPa.s when analyzed with a Brookfield LVT and spindle sp3 at 12 rpm.
12. Use of an emulsion according to any one of claims 1-11 as a source of free radicals.
- 25 13. Use according to claim 12 wherein the free radicals are used in a polymerization process.
- 30 14. Use according to claim 13 wherein vinyl chloride is polymerized, optionally together with other monomers and/or in the presence of a polymer.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 98/04015

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C07C409/00 C08F4/34 C08F14/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C07C C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 950 422 A (TORENBEEK REINDER ET AL) 21 August 1990 see the whole document	1
A	PATENT ABSTRACTS OF JAPAN vol. 013, no. 592 (C-671), 26 December 1989 & JP 01 249132 A (NIPPON OIL & FATS CO LTD), 4 October 1989 see abstract	1
A	PATENT ABSTRACTS OF JAPAN vol. 011, no. 290 (C-447), 18 September 1987 & JP 62 086005 A (KAYAKU NUURII KK; OTHERS: 01), 20 April 1987 see abstract	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

15 October 1998

Date of mailing of the international search report

22/10/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Bonnevalle, E

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/04015

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DISCLOSED ANONYMOUSLY: "Non freezing, aqueous peroxide emulsions" RESEARCH DISCLOSURE., vol. 215, no. 21520, 1982, page 63 XP002049544 HAVANT GB see page 63	1
A	GB 2 068 008 A (KENOGARD AB) 5 August 1981 cited in the application see the whole document	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/04015

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4950422	A	21-08-1990	US 5260390 A	09-11-1993
			US 5369197 A	29-11-1994
GB 2068008	A	05-08-1981	SE 435844 B	22-10-1984
			AU 522909 B	01-07-1982
			BE 887249 A	27-07-1981
			CA 1160618 A	17-01-1984
			CH 644135 A	13-07-1984
			DE 3102781 A	04-02-1982
			FI 810214 A,B,	29-07-1981
			FR 2474509 A	31-07-1981
			JP 56110703 A	02-09-1981
			JP 58051002 B	14-11-1983
			NL 8100378 A,C	17-08-1981
			SE 8000669 A	29-07-1981
			US 4499250 A	12-02-1985
			US 4547481 A	15-10-1985